



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

CHAMAL

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WEB
 WWW.CHAMAELEON-PRODUKTION.DE

#### TECHNICAL DATA SHEET

#### CHAMÄLEON ALUMINUM FILLER

Article number:

**Intended use:** 

**General characteristics:** 

# Knife filler/ Surfacer

15042, 15044, 15045, 15046, 15049

For car repair, engine construction and for hobby works. Everywhere, where a large-area spreading is desired. Applicable on galvanized sheets, aluminium and its alloys, iron, steel plates, wood, concrete.To fill and level out holes and to stabilise flimsy spots. Chamaeleon Aluminum Polyester Putty is a 2-component polyester filling putty as mixture of a medium-elastic, highly reactive, amino-preaccelerated polyester resin with different mineral, environment-friendly fillers and aluminium pigments.

# **Quality and properties:**

- Ease of working
- High elasticity
- Highly thixotropic, therefore very easy widespread and pore-free application
- Easy to sand
- Very good adherence
- Free of asbestos and silicone
- Short curing time
- Resistant to weak acids and bases, propellants, solvents, water and de-icing salt

# **Technical characteristics:**

**Basis:** 

Colour: Smell: Consistence: polyester resin with mineral fillers and aluminium pigments grey styrol soft, thixotropic, pasty

Chamäleon GmbH - Technical Data Sheet





CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WEB
 WWW.CHAMAELEON-PRODUKTION.DE

Pot life / Working time at 20°C: Working temperature: Drying time (at 20°C, 50% relative air humidity): Flash point: Density at 20°C:

Addition of hardener: Temperature resistance of the cured material: approx. 4 minutes min. 12°C

can be sanded after approx. 20 - 30 minutes approx. 33°C (resin); not applicable for hardener putty 1.65 g/cm<sup>3</sup> hardener 1.15 g/cm<sup>3</sup> 2 - 4 % (optimal mixture 2,5 %)

120°C

# **Application:**

Before use, carefully read and observe the warning texts on the label!

- The object you wish to repair should be de-rusted, clean, dry, fat-free and sanded.
- Take the requested portion of putty compound out of the can and mix it well with the corresponding quantity of hardener.
- Apply the mixed material in the desired layer thickness.
- Clean tools immediately after use, if necessary with a nitro thinner.
- Do not return mixed material into the can.
- After approx. 20-30 minutes the repaired spot can be drilled, sanded, sawed, rasped and painted.

#### **Environment and labeling:**

Environmentally sound:	The product is 100% free of heavy metals. The caps and packagings are made of recyclable material.
Disposal:	Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".
Storage stability:	18 months if appropriate storage provided (= $10^{\circ}$ -25°C, relative air humidity of max. 60%) in the unopened original container. Protect from direct sunlight, frost and humidity.





CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMĂLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

 FON
 0049 (0) 6221 - 520 440

 FAX
 0049 (0) 6221 - 520 449

 MAIL
 INFO@CHAMAELEON-PRODUKTION.DE

 WEB
 WWW.CHAMAELEON-PRODUKTION.DE

15042	Chamaeleon Aluminum Polyester Putty	250 g
15044	Chamaeleon Aluminum Polyester Putty	512 g
15045	Chamaeleon Aluminum Polyester Putty	1000 g
15046	Chamaeleon Aluminum Polyester Putty	1850 g
15049	Chamaeleon Aluminum Polyester Putty	4100 g

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety Data Sheet.