

TECHNICAL DATA SHEET*Revision date: 21.10.2022***AEROSOL PRIMER**

Article number:	26002, 26003, 26004, 26005
Colour:	Black, white, grey, red
Intended use:	Car refinishing product/ Primer, anticorrosion additive
General characteristics:	For the treatment of surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and plastics (PU, ABS, PC and PS). Suitable primer as pre-treatment for re-spraying with all lacquer systems (alkyd resin, nitro cellulose, 1-K acrylic and 2-K acrylic lacquers).
Product characteristics:	<ul style="list-style-type: none">▪ Fast drying▪ Excellent coverage and filling property▪ Corrosion preventive▪ Easy to sand, both wet and dry (from grain 400)▪ Re-sprayable with all lacquer systems
Technical characteristics:	
Contents:	500 ml
Base:	Nitro-cellulose binder
VOC-content:	Approximately 85% w/w
Solid content:	Approximately 15% w/w
Coverage:	1,5 to 2 m ²
Dust dry:	After 5 - 10 minutes
Tack free:	After 10 - 20 minutes
Hardened/re-sprayable:	After 2 hours
Heat resistant:	To 110°C

Processing conditions:

Please only use in an adequately ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

Usage:



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

Before use, carefully read the directions on the packaging and act accordingly.

Pre treatment:

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

Treatment:

The aerosol should have room temperature. Best processing temperature is between 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated should be approximately 25 - 30 cm.

Application:

Apply the primer in several thin layers. Before applying the next layer, again shake the aerosol.

After use:

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.

STEUERNUMMER/TAX NR.: DE 231468544
EORI NR./CUSTOMS NR.: DE 6029442 / HRB 9778
GESCHÄFTSFÜHRER/CEO: SASCHA HAGEMANN

BANK HEIDELBERGER VOLKSBANK EG
IBAN DE78 6729 0000 0042 8627 03
BIC GENODE61HDI